

Interference of a first-order transition with the formation of a spin-Peierls state in α' - NaV_2O_5 ?

M. Köppen, D. Pankert, and R. Hauptmann

*Institute of Solid State Physics, SFB 252, Darmstadt University of Technology,
D-64289 Darmstadt, Germany*

M. Lang, M. Weiden, C. Geibel, and F. Steglich

*Max-Planck-Institute of Chemical Physics of Solids,
D-01187 Dresden, Germany*

(February 1, 2008)

We present results of high-resolution thermal-expansion and specific-heat measurements on single crystalline α' - NaV_2O_5 . We find clear evidence for two almost degenerate phase transitions associated with the formation of the dimerized state around 33 K: A sharp first-order transition at $T_1 = (33 \pm 0.1)$ K slightly below the onset of a second-order transition at $T_2^{\text{onset}} \approx (34 \pm 0.1)$ K. The latter is accompanied by pronounced spontaneous strains. Our results are consistent with a structural transformation at T_1 induced by the incipient spin-Peierls (SP) order parameter above $T_2 = T_{\text{SP}}$.

PACS numbers: 75.40.Cx, 75.10.Jm, 65.70.+y

I. INTRODUCTION

The discovery of a spin-Peierls (SP) transition in the inorganic compound CuGeO_3 by Hase *et al.*¹ has triggered a large amount of investigations concerning the physical characteristics of the SP phase transition. A detailed analysis of the magnetic susceptibility showed that CuGeO_3 actually behaves differently from an ideal SP system. A significant next-nearest-neighbor coupling has to be invoked to understand the magnetic properties of this compound².

Recently, Isobe and Ueda³ reported susceptibility results on another inorganic system, polycrystalline α' - NaV_2O_5 , which shows a similar rapid decrease in the magnetic susceptibility below 34 K. This feature together with the existence of a broad maximum in the susceptibility around 350 K which closely follows the prediction for an $S = \frac{1}{2}$ antiferromagnetic Heisenberg chain led the authors to propose α' - NaV_2O_5 as a possible new SP compound.

In fact, the isotropic decrease of the magnetic susceptibility found for single crystalline material⁴, the occurrence of a lattice distortion below the transition temperature as observed by X-ray⁵, Raman-scattering⁴, thermal-expansion⁶ and NMR-measurements⁷ as well as the formation of a gap in the magnetic-excitation spectrum³ are prominent characteristics of a spin-Peierls transition. In general, for such a phenomenon to take place, the presence of spin-1/2 chains is considered a necessary condition. From early structural investigations on polycrystalline material a one-dimensional (1D) magnetic character was inferred⁸, implying two kinds of V chains running parallel to the b axis, one of which is formed by magnetic ($S = 1/2$) V^{4+} , the other one by nonmagnetic V^{5+} ions. Such a charge-ordered state at $T = 300$ K, however, was found to be incompatible with recent results of Raman-scattering experiments⁹. Moreover, a refined analysis of room temperature X-ray data indicate the existence of

only one distinct V site¹⁰, posing the question whether a 1D magnetic structure is actually realized in this system. So far, most of the work on α' - NaV_2O_5 was aiming at an investigation of the magnetic and structural aspects whereas little is known about the thermodynamic properties. In this paper we will present results of thermal-expansion and specific-heat measurements on an α' - NaV_2O_5 single crystal focussing on the phase transition into the nonmagnetic low-T state.

II. EXPERIMENTAL

Single crystals of α' - NaV_2O_5 were grown by slowly cooling a mixture of NaVO_3 and VO_2 with a molar ratio of 10:1 in an evacuated quartz tube. This assures that the melt is always Na rich - a condition necessary to achieve a Na content $x=1$, the highest possible Na concentration in α' - $\text{Na}_x\text{V}_2\text{O}_5$ ¹¹. This is especially important as the magnetic properties of α' - $\text{Na}_x\text{V}_2\text{O}_5$ are strongly x dependent: already a slight Na deficiency removes the SP transition completely⁴. The sample was cooled down from 800°C with a cooling rate of 1 K/h. The single crystals grown by this method could be easily separated from the NaVO_3 -flux by boiling the obtained sample in water since NaVO_3 only is soluble in hot water. The susceptibility of the single crystal (with outer dimensions $a \times b \times c = 1.17 \times 5.25 \times 0.29 \text{ mm}^3$ and mass $m = 5.41 \text{ mg}$) selected for the present investigations shows a sharp transition at $T_{\text{SP}} \approx 33 \text{ K}$, accompanied by a rapid and isotropic decrease in $\chi(T)$ towards lower temperatures (not shown). The small upturn in $\chi(T)$ for $T \rightarrow 0$ is ascribed to the presence of impurities (or defects). Assuming their effective spin to be $S = 1/2$, their concentration is estimated to be $< 0.05\%$, reflecting the high quality of the crystal.

The thermal expansion was measured by means of

an ultra-high-resolution capacitance dilatometer¹² with a maximum sensitivity of $\Delta l/l=10^{-10}$. Length changes $\Delta l(T)=l(T)-l(4.2\text{ K})$ were detected employing a heating rate $\frac{dT}{dt} \leq 2.5\text{ K/h}$. The coefficient of thermal expansion $\alpha(T) = \frac{1}{l(T)} \frac{dl}{dT}$ was approximated by the differential quotient $\alpha(T) \approx \frac{\Delta l(T_2)-\Delta l(T_1)}{l(300\text{ K}) \cdot (T_2-T_1)}$ with $T=(T_1+T_2)/2$. Measurements were performed along the three principal axes. The specific heat was measured using an AC-calorimeter¹³. A resistance heater is fed by an AC-power with frequency $f/2$ causing the temperature of the sample to oscillate with f . Within an appropriate range of frequencies, the amplitude of the temperature oscillation, T_{AC} , is inversely proportional to the heat capacity, $C(T)$, of the sample. T_{AC} was determined using a lock-in amplifier. The calorimeter was calibrated by measuring a sample of pure copper.

III. THERMAL EXPANSION

Figure 1 gives a survey of the linear thermal-expansion coefficient for $T \leq 200\text{ K}$ measured along the three principal axes. The data reveal a pronounced anisotropy consistent with the results of an X-ray study³. While the c-axis expansivity is extraordinarily large with a broad maximum around 175 K, the b- ('in-chain direction') and a-axis expansion coefficients are very small for temperatures $40\text{ K} \leq T \leq 250\text{ K}$. A blow-up of the data (cf. inset fig. 1) shows that α_a and α_b are negative up to about 150 K yielding a broad minimum around 85 K and 75 K, respectively. The low-temperature $\alpha(T)$ behavior is dominated by sharp phase-transition anomalies around the spin-Peierls transition temperature $T_{SP} \approx 33\text{ K}$. Figures 2 a-c give details of $\alpha(T)$ near T_{SP} along the three principal axes (note the different scales). Along the a- and c-axis we find large λ -type phase-transition anomalies of comparable magnitude but opposite signs. A striking feature of both data sets is the steepening of the slope of $\alpha(T)$ on the low-T side of the transition, i. e. slightly below the temperature of the $\alpha(T)$ extremum. As becomes more evident from the b-axis expansivity data (fig. 2c) we assign this behavior to the combined effects of two phase transitions, which are almost degenerate in temperature (see discussion in section V): An extremely sharp phase-transition anomaly (at T_1) located right at the middle of a somewhat broadened one (at T_2). While the two corresponding phase-transition anomalies are positive for α_a and negative for α_c , they have opposite signs for α_b . Moreover, a careful inspection of the $\alpha(T)$ data along the three axes shows that the sharp peak is actually split up into two very sharp structures separated by only 200 mK. This is exemplarily shown for the b-axis data in the inset of fig. 2. To exclude the possibility that this fine structure is caused by inhomogeneities in the Na content, further experiments on an independently prepared single crystal are in preparation.

The influence of a magnetic field of $B=8\text{ T}$ applied paral-

lel to the b-axis on α_b is shown in fig. 3. Surprisingly, the field does not lead to a homogenous shift of the two transitions towards lower temperatures. Rather it acts quite differently on both sides of the transition at T_1 : While the high-temperature flank of the second-order transition (as e. g. , its onset temperature T_2^{onset}) shows a comparatively strong reduction of $\Delta T_2^{onset} = -(0.36 \pm 0.1)\text{ K}$, no significant field dependence is found for α_b for temperatures below T_1 , i. e. for $T \leq 32.2\text{ K}$. Compared to the effect on T_2^{onset} , T_1 shows a much weaker field dependence of only $\Delta T_1 = -(0.13 \pm 0.1)\text{ K}$.

In order to clarify the nature of the two transitions and to separate their respective contributions, we plot in figs. 4 and 5 the relative length changes, $\Delta l_i/l$, for $i = a, b$ and c on the same temperature scale. As becomes obvious from fig. 4, the ordering phenomenon below 33 K is accompanied by the appearance of pronounced spontaneous strains with large and partly compensating effects along the c- and a-axis and an only minor length change along the b-axis. Besides this continuous lattice distortion, a detailed inspection of the data close to the transition provides evidence for the first-order character of the sharp structure in $\alpha(T)$ (cf. fig. 5). This becomes most clear for the b-axis data, where upon lowering the temperature a sudden elongation occurs within a rather small temperature interval of only 0.45 K centered around $T_1 = (33.0 \pm 0.1)\text{ K}$. This first-order transition is superimposed on the continuous change in the slope of $\Delta l/l$ from positive ($\alpha_b > 0$) for $T < 32.7\text{ K}$ to negative ($\alpha_b < 0$) for $T > 33.25\text{ K}$, which corresponds to the somewhat broadened second-order transition. We stress that in subsequent runs both transitions (including the splitting of the transition at T_1) could be reproduced in detail without any significant hysteresis at T_1 upon cooling and warming through the transition temperature.

By projecting the finite width of the transition at T_1 on the a- and c-axis data (vertical lines in fig. 5), one can clearly identify first-order-like behavior, i. e. sudden length changes, in the $\Delta l/l$ data also for the latter two axes.

For the determination of T_2 , the transition temperature of the second-order phase transition, we use the b-axis data where, due to their opposite signs, both transitions can be most clearly separated from each other. By simply subtracting in fig. 2c the sharp anomaly at T_1 from the $\alpha_b(T)$ data and replacing the remaining broadened transition by an idealized sharp one we find $T_2 = (32.7 \pm 0.1)\text{ K}$. We note that a non-vanishing contribution of the transition at T_1 to $\alpha(T)$ at lower temperatures (neglected in the above procedure) might shift T_2 to slightly higher values.

Our observation of pronounced spontaneous strains below T_2 indicate a substantial coupling between magnetic and lattice degrees of freedom for the present system. Within a Landau theory this coupling can be treated by adding to the Gibbs free energy an interaction term

$$G_{int} = \sum_{mn} \xi_{i,m,n} \epsilon_i^m Q^n \quad (m, n \in \mathcal{N}), \quad (1)$$

where $\xi_{i,m,n}$ are the coupling constants between the order parameter Q and the strain elements ϵ_i along the i th direction. In general, within the constraints given by the symmetry of the system, different coupling types ($n, m > 0$) may be possible. For a linear-quadratic strain-order-parameter coupling, $\xi_i \epsilon_i Q^2$, as e.g., realized in CuGeO_3 ¹⁵, the condition of a stress-free system then yields $\epsilon_i(T) \propto Q^2(T)$, i.e. the spontaneous strains vary as the square of the order parameter. To extract the ϵ_i ($i=a, b, c$), associated with the spin-Peierls transition, for the present system one has to subtract from the $\Delta l_i/l$ data (cf. fig. 4) the non-relevant background contribution. To this end we employed a smooth extrapolation of the $\Delta l/l$ data from $T > T_2$ into the low- T phase. Although, due to the rather high transition temperature substantial uncertainties have to be invoked for the background contribution, an only minor effect is found as for the conclusion drawn below. The resulting spontaneous strains normalized to their respective values at 4 K are plotted in fig. 6 as a function of reduced temperature $\frac{T_2-T}{T_2}$ on logarithmic scales. For all three axes we find power-law behavior, $\epsilon_i \propto \left(\frac{T_2-T}{T_2}\right)^\gamma$, over almost one decade in temperature. Deviations at low temperatures are likely to be caused by uncertainties in the background contribution. The tendency towards smaller exponents visible for temperatures close to the transition is assigned to the influence of one-dimensional fluctuations. From the slopes of the linear parts in fig. 6 the exponent γ can be determined. Most surprisingly, the γ -values for the a-, b- and c-axis strains of respectively (0.23 ± 0.05) , (0.7 ± 0.15) and (0.36 ± 0.1) differ significantly from each other. In particular γ_b , the exponent for the 'in-chain' strain is strongly enhanced - the same tendency, although much less pronounced was found also for CuGeO_3 ¹⁵. As for the origin of this behavior one may think of (i) an anisotropy in the coupling constants $\xi_{i,m,n}$ which causes different exponents in the leading terms of eqn. 1 along the various axes or (ii) a finite coupling to the order parameter of the first-order transition. Since for the b-axis, the $\alpha(T)$ anomalies associated with the respective transitions at T_1 and T_2 have opposite signs, the one at T_2 being comparatively small, a rather strong influence of the lattice distortion at T_1 on ϵ_b appears plausible.

A further observation made in the present thermal-expansion study is worth mentioning: A comparison of the volume-expansion coefficient, β , as determined from the present measurements on single crystalline material, $\beta_{sc} = \alpha_a + \alpha_b + \alpha_c$, with that derived from polycrystalline samples, $\beta_{pc} = 3 \cdot \alpha_{pc}$, reveals striking discrepancies (see ref. 6 for α_{pc}). Although T_{SP} is almost identical for the two variants, the absolute value as well as the temperature variation of β is strikingly different both at and above T_{SP} . A similar observation was already

made for CuGeO_3 (see ref. 14 and 15 for poly- and single-crystalline samples, respectively). Up to now we have no explanation for this discrepancy. Texture effects in the polycrystal used in ref. 14 at the origin of this problem can be safely excluded¹⁶.

IV. SPECIFIC HEAT

In order to give a full thermodynamical analysis of the two coexisting phase transitions, we have performed supplementary measurements of the specific heat, $C(T)$, on the same single crystal in the temperature range $1.8\text{ K} \leq T \leq 60\text{ K}$. Fig. 7a shows the specific heat as $C(T)$ vs T over the whole temperature range investigated. The SP transition manifests itself in the sharp maximum around 33 K. An excellent fit of the low-temperature data, i.e. $T \leq 12\text{ K}$, is provided by adding to the phonon term $C_{ph} = \beta \cdot T^3$ a magnetic contribution $C_{mag} = a \exp(-\Delta/T)$, which corresponds to singlet-triplet excitations across an energy gap Δ . For the zero-temperature value we find $\Delta = (84 \pm 10)\text{ K}$, in good agreement with the results from measurements of the magnetic susceptibility $(85 \pm 15\text{ K})$ ¹⁴, the nuclear magnetic resonance (98 K) ⁷, as well as the electron-spin resonance $(92 \pm 20\text{ K})$ ²⁰ and $(85 \pm 20\text{ K})$ ¹⁷. These values are slightly smaller than $\Delta = 114\text{ K}$ derived from inelastic neutron-scattering experiments⁵. Fig. 7b shows details of $C(T)$ around 33 K as $C(T)/T$ vs T . With the knowledge of $\alpha(T)$ (fig. 2) one might also separate two different contributions to $C(T)$: A sharp maximum associated with the first-order transition at T_1 (width of shaded area in fig. 7b is taken from the anomaly in $\alpha_b(T)$ at T_1 , cf. fig. 2c) superimposed on a somewhat broadened second-order transition at T_2 . We stress that as a consequence of the AC technique employed here implying temperature oscillations of the sample of $\pm 50\text{ mK}$ at $T = 33\text{ K}$, sharp structures become necessarily broadened in our $C(T)$ data compared to $\alpha(T)$.

V. DISCUSSION

The results presented in the preceding paragraphs suggest the existence of two closely spaced phase transitions associated with the formation of a dimerized state in α' - NaV_2O_5 around 33 K: A sharp first-order transition at $T_1 = (33.0 \pm 0.1)\text{ K}$ slightly above a continuous phase transition at $T_2 = (32.7 \pm 0.1)\text{ K}$.

As an alternative interpretation one might think of the possibility that the observed features reflect a *single* phase transition which is of weakly first order. Since the b-axis $\alpha(T)$ data around the transition temperature reveal two anomalies of opposite signs, this scenario implies that the sharp but small negative peak in α_b must be a 'secondary effect' caused - via the three-dimensional

elastic couplings - by the much larger effects in the orthogonal directions. As will be discussed below, however, this interpretation appears incompatible with the field dependence of α_b and is thus discarded.

The occurrence of spontaneous strains below T_2 suggests that the latter transition is driven by the strain-order-parameter coupling resulting in the formation of a gap in the spin-excitation spectrum, i. e. $T_2 = T_{SP}$. Then the questions at hand are: (i) what is the nature of the first-order transition and (ii) what is its role in the formation of the spin-Peierls ground state? As for the nature of the transition at T_1 it is tempting to assign this effect to a structural transformation. The substantial magneto-elastic coupling, as highlighted by the pronounced spontaneous strains below T_{SP} , then naturally implies a coupling of both order parameters.

As a possible scenario we propose that, upon lowering the temperature, the incipient spin-Peierls order parameter induces via strain-order-parameter coupling a structural transition at T_1 . The latter then stabilizes the spin-Peierls transition. Note that along the a- and c-axis, where the dominant effect on the lattice is observed upon cooling below 33 K, the length changes associated with the transition at T_1 , $\Delta l|_{T_1}$, proceed along the same direction as ϵ_a and ϵ_c , respectively (cf. fig. 5). The above assignment of the two transitions is also consistent with the response in α_b when a magnetic field of 8 T is applied along the b-axis (cf. fig. 3): While the onset of the transition at T_2 shows a significant reduction of $\Delta T_2^{onset} = -0.36$ K, T_1 is only slightly reduced in this field by $\Delta T_1 = -0.13$ K. Even more striking is the fact that the low-T end of the continuous transition at T_2 , i. e. $\alpha_b(T)$ for $T < T_1$, does not show any significant field dependence at all. These shifts have to be compared with the field-induced reduction, ΔT_{SP}^{cal} , expected for an ideal spin-Peierls transition¹⁸ and actually found for all known spin-Peierls systems^{19,1}. Employing the results of a Hartree-Fock approximation

$$\frac{T_{SP}^{cal}(H) - T_{SP}(0)}{T_{SP}(0)} = -a \left(\frac{g_b \mu_B H}{2k_B \cdot T_{SP}(0)} \right)^2 \quad (2)$$

where $g_b = 1.972$ is the g-factor²⁰, μ_B the Bohr magneton, k_B the Boltzmann constant and $a = 0.44$ ¹⁸, we find $\Delta T_{SP}^{cal} = -0.375$ K. From the excellent agreement with the experimentally observed reduction of T_2^{onset} we infer that the high-T side of the transition, i. e. at $T > T_1$, reflects the behavior of a common spin-Peierls transition. The much weaker field dependence of T_1 and the almost field-independent behavior below T_1 rule out the possibility that the sharp feature in α_b at T_1 is a secondary effect caused by the pronounced anomalies in the orthogonal directions. In this case a homogenous shift of the two features at T_1 and T_2 in a magnetic field would be expected. Rather it indicates the action of another interfering mechanism.

A direct proof of our assignment of two phase transi-

tions would be provided by pressure experiments, where uniaxial strain is applied along the b-axis. From the different signs of the phase-transition anomalies $\Delta\alpha_b$ and Δl_b associated with the respective transitions at T_1 and T_2 , a pressure-induced separation of the transitions can be expected: Applying the Ehrenfest-relation and the Clausius-Clapeyron equation to the second- and first-order transition, respectively, we predict a positive pressure dependence of the transition at T_2 ($(\frac{\partial T_2}{\partial p_b})_{p_b \rightarrow 0} > 0$) and a negative pressure dependence for the first-order transition ($(\frac{\partial T_1}{\partial p_b})_{p_b \rightarrow 0} < 0$).

In conclusion, thermodynamical investigations on α' - NaV_2O_5 reveal indications for two almost degenerate phase transitions around 33 K associated with the formation of a nonmagnetic ground state. The second-order transition at $T_2 = (32.7 \pm 0.1)$ K shows the signatures of a SP transition as to the occurrence of spontaneous strains and the field dependence of its onset temperature. In this sense we assign the first-order transition at $T_1 = (33 \pm 0.1)$ K to a structural transformation induced by the incipient SP order parameter at $T > T_2$. In general, for this phenomenon to take place, the existence of spin-1/2 chains is considered a necessary condition. In light of the results of recent structural investigations at room temperature which are inconsistent with the above requirements a detailed T-dependent determination of the magnetic structure appears badly needed.

Acknowledgment

This work was supported by the BMBF grant No. 13N6608/1.

-
- ¹ M. Hase, I. Terasaki, and K. Uchinokura, *Phys. Rev. Lett.* **70**, 3651 (1993).
 - ² G. Castilla, S. Chakravarty, and V. J. Emery, *Phys. Rev. Lett.* **75**, 1823 (1995).
 - ³ M. Isobe and Y. Ueda, *J. Phys. Soc. Jpn.* **65**, 1178 (1996).
 - ⁴ M. Weiden, R. Hauptmann, C. Geibel, F. Steglich, M. Fischer, P. Lemmens, and G. Güntherodt, *Z. Phys. B* **103**, 1 (1997).
 - ⁵ Y. Fujii, H. Nakao, T. Yoshihama, M. Nishi, K. Nakajima, K. Kakurai, M. Isobe, Y. Ueda, and H. Sawa, *J. Phys. Soc. Jpn.* **66**, 326 (1997).
 - ⁶ M. Weiden, R. Hauptmann, C. Geibel, M. Köppen, J. Müller, M. Lang, F. Steglich, N. Weiden, M. Fischer, P. Lemmens, G. Güntherodt, *Physica B* in press.
 - ⁷ T. Ohama, M. Isobe, H. Yasuoka, and Y. Ueda, *J. Phys. Soc. Jpn.* **66**, 545 (1997).

- ⁸ A. Carpy and J. Galy, *Acta Crystallogr. Sect. B* **31**, 1481 (1975).
- ⁹ M. Fischer, G. Els, P. Lemmens, G. Güntherodt, A. S. Mishenko, M. Weiden, R. Hauptmann, C. Geibel, F. Steglich to be published.
- ¹⁰ H. G. von Schnering, to be published.
- ¹¹ M. Pouchard, A. Casalot, J. Galy, P. Hagenmuller, *Bull. Soc. Chim. France* **11**, 4343 (1967).
- ¹² R. Pott and R. Schefzyk, *J. Phys. E* **16**, 445 (1983).
- ¹³ P. F. Sullivan and G. Seidel, *Phys. Rev.* **173**, 679 (1968).
- ¹⁴ M. Weiden, J. Köhler, G. Sparr, M. Köppen, M. Lang, C. Geibel, and F. Steglich, *Z. Phys. B* **98**, 167 (1995).
- ¹⁵ H. Winkelmann, E. Gamper, B. Büchner, M. Braden, A. Revcolevschi, and G. Dhalenne, *Phys. Rev. B* **51**, 12884 (1995).
- ¹⁶ M. Köppen, to be published.
- ¹⁷ W. Palme, S. Schmidt, B. Lüthi, J. P. Boucher, M. Weiden, R. Hauptmann, C. Geibel, A. Revcolevschi, G. Dhalenne, *Physica B* in press.
- ¹⁸ L. N. Bulaevski, A. I. Buzdin, and D. I. Khomski, *Sol. State Commun.* **27**, 5 (1978).
- ¹⁹ J. W. Bray, L. V. Interrante, I. S. Jacobs, and J. C. Bonner, in *Extended Linear Chain Compounds* edited by J. S. Miller (Plenum Press, New York, 1982) p. 353.
- ²⁰ A. N. Vasil'ev, A. I. Smirnov, M. Isobe, and Y. Ueda, *Phys. Rev. B* in press.

FIG. 1. Coefficient of thermal expansion, α , vs T along the three orthorhombic crystal axes. Inset: blow up of α vs T for the a - and b -axis.

FIG. 2. Coefficient of thermal expansion, α , vs T for $28\text{ K} < T < 37\text{ K}$ along the various axes. Inset shows details of the negative peak in α_b on expanded scales.

FIG. 3. Coefficient of thermal expansion, α_b , for $B=0$ ($\square$) and $B=8\text{ T}$ ($\bullet$), applied parallel to the b -axis. Lines are guides to the eyes. Data points around the double structure near T_1 have been omitted for clarity.

FIG. 4. Relative length changes $\Delta l/l$ vs T along the three crystal axes shifted so that the curves meet at 35 K .

FIG. 5. Relative length change $\Delta l/l$ vs T on expanded scales close to the SP transition. Vertical lines indicate the temperature range of the first-order transition.

FIG. 6. Normalized spontaneous strains vs reduced temperature on logarithmic scales. Solid lines represent fits of the form $\epsilon \propto (1 - T/T_2)^\gamma$.

FIG. 7. Specific heat, $C(T)$, as C vs T (a) and $C(T)/T$ vs T (b). Width of shaded area in (b) indicates the temperature range of the first-order transition as determined from $\alpha(T)$ measurements.













